

## IN THE CLAIMS:

1. (original) A process for preparing breathable, elastic polyolefin films, including the steps of:
  - blow molding a mixture of olefins, styrenic thermoplastic elastomers and filler to facilitate the generation of porosity by stretching;
  - squeezing the tubular to obtain a flat film;
  - heating the flat film to the softening point;
  - pressing the flat film;
  - cooling the flat film to a temperature of 8 to 30°C;
  - stretching the film in the transverse and/or longitudinal directions to make it breathable.
2. (original) A process as claimed in claim 1, further comprising the steps of:
  - coupling a separating material to the breathable elastic film;
  - winding the film coupled with the separating material, into a roll.
3. (currently amended) A process as claimed in claim 1 ~~or 2~~, wherein said mixture comprises 30% to 70% by weight fillers, 10% to 40% by weight styrenic thermoplastic elastomers and 10% to 50% by weight olefins.
4. (currently amended) A process as claimed in claim 1 ~~, 2 or 3~~, wherein said separating material has a continuous structure.
5. (original) A process as claimed in claim 4, wherein said separating material is a paper or nonwoven fabric film.
6. (original) A process as claimed in claim 5, wherein said paper or nonwoven fabric film is coupled to said extruded film by an adhesive.

7. (original) A process as claimed in claim 5, wherein said paper or nonwoven fabric film is coupled to said extruded film (11) without using adhesives.
8. (currently amended) A process as claimed in claim 1,~~2 or 3~~, wherein said separating layer has a discontinuous structure.
9. (original) A process as claimed in claim 8, wherein said separating layer is made of a powdered material.
10. (original) A plant for producing a breathable elastomeric polyolefin film, including, in succession:
  - a blow molding extruder (1) for extruding a tubular (11);
  - a calender (2) for squeezing the extruded tubular (11) fed from the blow molding extruder;
  - means (3, 4) for heating the squeezed extruded tubular film to the softening point;
  - a calender (5) to press the film that was previously heated to the softening point;
  - means (5) for cooling the compressed film to a temperature of 8 to 30°C;
  - means (6, 8) for stretching the film (11) in the transverse and/or longitudinal directions;
  - means (6, 8) for stretch stabilization by cooling the extruded film (11);
11. (original) A plant as claimed in claim 10, which further includes:
  - means (12, 13, 14) for coupling the extruded film (11) to a separating material;
  - a reeling machine (9) for winding the film (11) coupled to said separating material into a roll (18).
12. (original) A use of a mixture of olefins, styrenic thermoplastic elastomers and filler to produce a breathable elastic film.

13. (original) A use of a mixture as claimed in claim 12, wherein the amount of styrenic thermoplastic elastomers is of 10% to 40% by weight, the amount of filler is 30% to 70% by weight and the amount of olefins is of 10% to 50% by weight.
14. (new) A process as claimed in claim 2, wherein said mixture comprises 30% to 70% by weight fillers, 10% to 40% by weight styrenic thermoplastic elastomers and 10% to 50% by weight olefins.
15. (new) A process as claimed in claim 2, wherein said separating material has a continuous structure.
16. (new) A process as claimed in claim 3, wherein said separating material has a continuous structure.
17. (new) A process as claimed in claim 2, wherein said separating layer has a discontinuous structure.
18. (new) A process as claimed in claim 3, wherein said separating layer has a discontinuous structure.